



Physical properties

⑤

Item	Unit	EXCEL C21	FKM-70
Hardness (JIS.A)	point	72	70
Tensile Strength	MPa	13.6	13.6
Elongation	%	366	270
100% Modulus	MPa	3.0	4.5
Compression Set (P-26 O-ring 25% press)	200°CX70h	30	16
Upper limit operating temp.	°C	220	200
Amine		○	×
Ultra-low Particle generation		◎	×

◎ : No problem at all ○ : No problem ▲ : Need attention × : Cannot be used

Best Partner with Excellent Materials & Services